

RINOL *PU-S602AS*

Product description and use

RINOL PU-S602AS is a solvent-containing, coloured **UV-resistant, anti-slip, abrasion-resistant, anti-static** 2-component coating compound based on high-quality polyurethane resin having **very good cleaning abilities**. RINOL PU-S602AS is used as a matt sealant for hard, and tough and hard coating systems based on polyurethane and epoxy resins.

2 Laying Instructions

Substrate Preparation

The substrate must be clean and free from release agents. RINOL PU-S602AS can be applied to RINOL-PU and EP top coats.

In general it must be checked whether the substrate is open-pore, porous, etc. since in these cases bubbles and pores may be formed in the coating. This should be checked by the fabricator and remedied if necessary.

The matting must be applied, at the earliest, 24 hours after the application of previous coat at 20°C.

Care should be taken to ensure that no silicone-containing or other materials which could interfere with the reaction come into contact with RINOL PU-S602AS both before and during the curing phase.

Processing

The product is supplied in 2-component containers in the exact mixing ratio.

Before processing, the material must be heated at least to ambient temperature (room and floor temperature).

The A-component must be stirred briefly. Then the entire contents of the B-component are emptied into the A-component. Both components must be mixed homogeneously for at least 2–3 minutes using a suitable electric stirring tool. The inclusion of air in the stirring process must be avoided. The mixture should be poured into a different container and then stirred again briefly.

RINOL PU-S602AS is distributed, in portions, over the area of the surface to be sealed using a rubber spreader, although it is spread as thinly as possible, and is immediately rerolled using a foam roller. The formation of puddles during application is to be avoided.

Technical Data	
Liquid mixture (A+B)	
1. Packaged unit size (2-component container)	15 kg
2. Colour	See RINOL color chart (matt)
3. Shelf life/storage	6 months at 5–20°C always store above freezing and out of direct sunlight (even during transport)

Technical Data	
Liquid mixture (A+B)	
1. Processing time (20°C)	approx. 90 min
2. Processing/material/room temperature	approx. 15–25°C (min. 3 degrees above the dew point, even during laying and curing)
3. Relative humidity	< 75% (during the entire laying and curing phase)
4. Pre-reaction time	Not necessary
5. Material consumption (see processing instructions)	approx. 100–120 g/m ²
6. Can be walked on (20 °C)	after 18–24 hours
7. Full load-bearing capacity mechanical (20°C) chemical (20°C)	after 7 days after 28 days

Technical Data	
Cured material	
1. Abrasion resistance (BS 8204-2:2003 + A2:2011, BS EN 13892-4:2002)	<0,005 mm (3mm epoxy lining + 2 coats RINOL PU-S602AS)
2. Abrasion resistance (ASTM D4060-14)	<15 mg
3. Pencil hardness	5H
4. Surface resistivity	≤5x10 ⁶ Ω/square

Manufacturer

RCR Flooring Products Italia Srl, via V. Chiarugi 76/U, I-45100 Rovigo Tel +39-0425-411200 Fax +39-0425-411222

RINOL *PU-S602AS*

Maintenance

In order to preserve the properties of the synthetic resin floor covering in the long term, we recommend regular maintenance. Please ask for a copy of our RINOL maintenance guide for further information.

Possibilities for layering and more detailed information regarding the laying of RINOL products can be found in the RINOL Technical Guide.

Safety measures

For information on handling the product please refer to the valid safety data sheet and the Chemicals Regulations regarding the handling of coating materials (M004/M023). Suitable protective clothing and goggles must be worn during processing.

Skin contact with liquid resins can be harmful to health and may lead to allergies.

Note

The specification values given are approximate values ascertained by us and do not constitute guaranteed properties. Consequently, no liability claims may be derived from the product data sheet.

Please also note that only the most recent version of the technical data sheet is valid and replaces all previous data sheets.

Important note

In addition to ambient temperature, floor temperature is of key importance.

As a basic principle the chemical reactions are delayed at low temperatures. The reworking time and the time until the floor can be walked on are thus extended.

Higher viscosities of the products also cause an increase in material consumption.

At higher temperatures the chemical reactions are shortened and the reworking time and the time until the floor can be walked on are reduced.

As a basic principle, protect against the infiltrating action of moisture from the rear face, including during use.

Legal note:

Owing to the different materials, substrates and differing working conditions, no guarantee in terms of result or adhesion for whatever reason and/or legal nature can be assumed by RINOL.

For the rest, the most recent general terms of business of RCR Flooring Products apply and can be requested from us or viewed, in their most recent version, at www.rinol.com and printed out. We reserve the right to make changes to the product specifications.


Manufacturer

RCR Flooring Products Italia Srl, via V. Chiarugi 76/U, I-45100 Rovigo Tel +39-0425-411200 Fax +39-0425-411222

RINOL *PU-S602AS*

CE marking:

DIN EN 13813 "screed mortars, screed materials and screeds - properties and requirements" (Jan. 2003) specifies requirements of screed mortars which are used for floor constructions in interior spaces. This standard also covers synthetic resin coatings and sealants. Products which conform to the above-mentioned standard are provided with the CE marking.

 RINOL Italia Research & Technology Srl Via Chiarugi 76/U I-45100 Rovigo
05 ¹ EN 13813 SR-B1,5 -IR4



Synthetic resin screed/coating for internal use in buildings (superstructures in accordance with techn. data sheets)	
Reaction to fire	NPD ²
Water permeability	NPD ²
Bond	B 1.5
Impact resistance	IR 4
Impact sound insulation	NPD ²
Noise absorption:	NPD ²
Chemical resistance	NPD ²

- 1) the last two numbers of the year in which the CE marking was applied
- 2) NPD = no performance determined

CE marking: 1504-2

Flooring systems which are subjected to mechanical stresses and products thereof which comply with DIN EN 1504-2 must also satisfy the requirements of DIN EN 13813.

DIN EN 1504-2 "products and systems for the protection and maintenance of concrete structures – part 2: surface protection systems for concrete" specifies the requirements for the surface protection methods "hydrophobing impregnation", impregnation and coating. The relevant data sheet can be requested as necessary.

Manufacturer

RCR Flooring Products Italia Srl, via V. Chiarugi 76/U, I-45100 Rovigo Tel +39-0425-411200 Fax +39-0425-411222