

1 General data

Product description / Application

RINOL PU-S602AS is a solvent-based, pigmented, antistatic, UV resistant, abrasion resistant, 2-component coating compound based on high quality polyurethane resin with very good cleanability.

RINOL PU-S602AS is used as a matt sealer for hard and tough coating systems based on polyurethane and epoxy resins.

2 Installation instructions

Substrate preparation

The substrate must be clean and free of release agents. RINOL PU-S602AS can be applied to RINOL PU / EP topcoats.

It is essential to check whether the substrate is porous, porous or similar, as this can lead to the formation of bubbles or pores in the coating. This must be checked by the applicator and eliminated if necessary. The matt finish must be applied at 20°C at the earliest 24 hours after application of the underlying layer.

Ensure that no substances containing silicone or other substances that may interfere with the reaction come into contact with RINOL PU-S602AS before and during the curing phase.

Application

The product is supplied in co-ordinated quantities in 2-component containers. Before processing, the material must always be warmed to at least ambient temperature (room and floor temperature).

The A component must be stirred briefly. The B component is then completely emptied into the A component. Mix both components homogeneously for at least 2 - 3 minutes using a suitable electric mixer. Avoid stirring in air. The mixture should be decanted and then stirred again briefly.

RINOL PU-S602AS is spread in portions with a rubber squeegee over the entire surface to be sealed, but as thinly as possible, and immediately rolled over with a molletoptrene roller or short-pile lambskin roller. Avoid the formation of puddles during application.

Rerolling should be carried out crosswise to avoid rolling marks.

Maintenance

To maintain the properties of the synthetic resin floor covering in the long term, we recommend regular maintenance. Please ask for our RINOL care instructions.

Colour shade

Almost all colour shades are possible. Slight colour deviations are unavoidable due to the raw material. Colour deviations may occur permanently with light shades of colour, e.g. in the yellow or orange range, due to filling with quartz sand.

Protective measures

For information on handling the product, please refer to the valid safety data sheet and the guidelines of the chemical industry on handling coating materials (M004/M023). Suitable protective clothing and safety goggles

Technical data

Liquid mixture (A+B)

1	Container size (2-component container)	15 kg container
2	Colours	RINOL standard colours (matt)
3	Shelf life / storage	6 months at 15-20°C, always store frost-free (including during transport), protect from direct sunlight.

Technical data

Liquid mixture (A+B)

1	Processing time (20°C)	approx. 90 minutes
2	Processing / material and room temperature	15-25°C (min. 3 degrees above the dew point even during laying and curing)
3	Material consumption (follow laying instructions!)	approx. 60 - 150 g/m ²
4	Walkability (20°C)	after approx. 18 - 24 hours
5	Rel. humidity	< 75% during the entire laying and curing phase

Technical data

Cured material

1	Adhesive strength (DIN ISO 4624)	> 1.5 N/mm ²
2	Resistance to earth (DIN EN 61340-4-1)	R _g < 10 ⁹ Ω
3	Full load-bearing capacity mechanical (20°C) chemical (20°C)	after 7 days after 28 days

must be worn during processing.

Skin contact with liquid resins can lead to health problems and allergies.

Note

Due care has been taken in compiling the technical data for the company's products. However, any recommendations or suggestions made with regard to the use of these products are made without guarantee, as the conditions under which they are used are beyond the company's control. It is the responsibility of the customer to check whether the products are suitable for the respective application and whether the conditions of use are appropriate for the respective product. No liability claims can therefore be derived from the product data sheet.

We would also like to point out that only the latest version of the data sheet is valid and replaces all older data sheets. The technical data given are approximate values determined by us and do not constitute a guarantee of properties. Misprints, errors, translation errors and changes reserved. Please note that the information in the system data sheets of the different languages / countries may differ. Further information can be found on our

RINOLPU-S602AS

UV RESISTANT ANTISTATIC COLORED POLYURETHANE TOPCOAT

RINOL

website at www.rinol.com

Chemically and mechanically stressed surfaces are subject to wear due to use. Regular maintenance is recommended. Consumption quantities, processing time, walkability and achievement of load-bearing capacity depend on temperature and object.

The technical data sheet does not exempt the user from carrying out his own tests - if necessary, within the scope of his possibilities - with regard to applicability. Please refer to the RINOL Technical Guide for layer structure options and more detailed information on the installation of RINOL products.

Important note

In addition to the ambient temperature, the floor temperature is of decisive importance.

Chemical reactions are generally delayed at low temperatures. This extends the recoating and walkability times. The higher viscosity of the products also increases material consumption.

At higher temperatures, the chemical reactions are shortened and the recoating and walkability times are reduced.

The material must always be protected from water during application. During application, care must be taken to ensure that no drops of sweat or water get into the fresh coating surface (foaming). Furthermore, the material must be protected from direct contact with water for approx. 24 hours (at 20°C) after application.

If there is a longer waiting time of >24 hours between the individual work steps or if surfaces already treated with liquid synthetic resins are to be coated again after a longer period of time, the old surface must be cleaned well, sanded thoroughly and vacuumed.

Applications that are not clearly mentioned in this technical data sheet may only be carried out after consultation and written confirmation with or by the application technology department of RCR Flooring Products Italia S.r.l..

Always protect against the effects of moisture on the back and from pressure, even during use.

Legal information:

Due to the different materials, substrates and deviating working conditions, no guarantee of a work result or liability can be assumed by RCR Flooring Products for whatever reason and / or legal relationship. In addition, the latest general terms and conditions of RCR Flooring Products Italia S.r.l. apply, which can be requested from us or viewed and printed out at www.rinol.com. We expressly reserve the right to make changes to the product specifications.

CE labelling:

DIN EN 13813 "Screed mortars, screed compounds and screeds - Characteristics and requirements" (Jan. 2003) specifies requirements for screed mortars used for indoor floor constructions.

Synthetic resin coatings and sealants are also covered by this standard. Products that comply with the above standard must be labelled with the CE mark.

CE

RCR Flooring Products Italia S.r.l.
Via Chiarugi 76/U
I-45100 Rovigo

05¹
EN 13813 SR-B1,5-IR4

1119-CPR-0833
09
EN 1504-2

Synthetic resin screed/coating for indoor use in buildings (structures according to technical data sheets)

Fire behaviour: NPD ²

Water permeability: NPD ²

Wear resistance (Abrasion Resistance): NPD ²

Tensile bond strength: B 1,5

Impact resistance IR 4

Impact sound insulation: NPD ²

Sound absorption: NPD ²

Chemical resistance: NPD ²

-1) the last two digits of the year in which the CE marking was affixed.

-2) NPD = No Performance Determined; characteristic value not specified

CE marking: 1504-2

Floor systems that are subject to mechanical stresses and whose products comply with DIN EN 1504-2 must also fulfil the requirements of DIN EN 13813.

DIN EN 1504-2 "Products and systems for the protection and repair of concrete structures - Part 2: Surface protection systems for concrete" specifies the requirements for the surface protection methods "hydrophobic impregnation", "impregnation" and "coating". If required, the corresponding data sheet can be requested.

GIS-Code: PU 50

Further information on the GIS code is available from Wingis online at <https://www.wingisonline.de>.