

RINOL PA-QC714

FAST CURING TRANSPARENT COATING FOR COLORED QUARTZ SAND

RINOL



1 General data

Product description / Application

RINOL PA-QC714 is a solvent-free, colourless, low-viscosity, fast-curing, ready-to-use 2-component coating and binder made of high-quality polyaspartic resin, UV-resistant.

RINOL PA-QC714 is used for solid and hard, non-porous, jointless final sealing on colored quartz sand.

The area of application includes supermarkets, breweries or production halls that are exposed to high freight loads as well as industrial kitchens, slaughterhouses or wet areas in the food industry.

2 Laying instructions

Substrate preparation

The substrate must be sufficiently load-bearing (compressive strength min. 25 N/mm²). The adhesive tensile strength must be at least 1.5 N/mm². Compatibility with older coatings must be checked by the user. Adhesion problems may occur with dense or hard surfaces if the substrate is not prepared accordingly. In this case, we recommend application on a test surface. It must also be free of oily, greasy or release agent-containing contaminants, loose particles, etc. In general, check whether the substrate is open-pored, porous, etc., as this could cause bubbles and pores in the coating. This should be checked by the user and rectified if necessary.

When applying the product, ensure that the tools and coating are absolutely clean.

It must be ensured that no silicone-containing or other reaction-interfering substances come into contact with RINOL PA-QC714 before and during the curing phase.

Application

The product is supplied in coordinated quantities in 2-component containers. Before processing, the material must always be warmed to at least ambient temperature (room and floor temperature). The A component must be stirred for at least 1-2 minutes. Then pour the complete contents of the B component into the A component and mix both components homogeneously for at least 2-3 minutes using a mechanical agitator. Avoid stirring in air. The material should be poured into another container and stirred again briefly.

RINOL PA-QC714 is spread in portions with a spatula or rubber squeegee and rolled on with a short pile roller.

Reworking

When reworking up to 5 hours after installation, further sanding is not necessary. Subsequent reworking is only possible after careful sanding and vacuuming of the sanding dust.

Maintenance

To maintain the properties of the synthetic resin flooring in the long term, we recommend regular maintenance. Please ask for our RINOL care instructions.

Protective measures

For information on handling the product, please refer to the valid safety data sheet and the guidelines of the chemical industry on handling coating

Technical data		
Liquid mixture (A+B)		
1	Container size (2-component container)	10 kg container
2	Colour	colourless
3	Shelf life / storage	6 months at 5-20°C, in any case (also during transport) frost-free, protect from direct sunlight

Technical data		
Liquid mixture (A+B)		
1	Density of binder (20°C)	approx. 1.10 g/cm ³
2	Processing time (20°C)	approx. 20 - 25 minutes
3	Processing / material and room temperature	5-25°C (min. 3 degrees above the dew point even during installation and curing)
4	Material consumption/ working cycle	approx. 200-600 g/m ²
5	Walkability (20°C)	after approx. 5 hours
6	Subsequent coating (20°C)	after approx. 3 - 5 hours
7	Rel. humidity	< 70% during the entire laying and curing phase

Technical data		
Cured material		
1	Adhesive peel strength (DIN ISO 4624)	> 1,5 N/mm ²
2	Full load-bearing capacity mechanical (20°C) chemical (20°C)	after 7 days after 28 days
3	Compressive strength (DIN EN 196 / ASTM C 109)	> 25 N/mm ²

materials (M004/M023). Suitable protective clothing and safety goggles must be worn during processing.

Skin contact with liquid resins can lead to health problems and allergies.

Notes

Due care has been taken in compiling the technical data for the company's products. However, all recommendations or suggestions made with regard to the use of these products are made without guarantee, as the conditions under which they are used are beyond the company's control. It is the responsibility of the customer to check whether the products are suitable for the respective application and whether the conditions of use are appropriate for the respective product. No liability claims can therefore be derived from



RCR Flooring Products Italia S.r.l.

Via V. Chiarugi 76/U
I - 45100 Rovigo

Tel.: +39 (0) 425 411 200
Fax: +39 (0) 425 411 222

info.italy@rcrif.com
www.rinol.com

COMPANY WITH
MANAGEMENT SYSTEM
CERTIFIED BY DNV
ISO 9001 - ISO 14001

RINOL PA-QC714

FAST CURING TRANSPARENT COATING FOR COLORED QUARTZ SAND

RINOL

the product data sheet.

We would also like to point out that only the latest version of the data sheet is valid and replaces all older data sheets. The technical data given are approximate values determined by us and do not constitute a guarantee of properties. Misprints, errors, translation errors and changes reserved. Please note that the information in the system data sheets of the different languages / countries may differ. Further information can be found on our website at www.rinol.com

Chemically and mechanically stressed surfaces are subject to wear due to use. Regular maintenance is recommended. Consumption quantities, processing time, walkability and achievement of load-bearing capacity depend on temperature and object.

The technical data sheet does not exempt the user from carrying out his own tests - if necessary within the scope of his possibilities - with regard to applicability. Please refer to the RINOL Technical Guide for layer structure options and more detailed information on the installation of RINOL products.

Important note

In addition to the ambient temperature, the floor temperature is of decisive importance.

Chemical reactions are generally delayed at low temperatures. This extends the recoating and walkability times. The higher viscosity of the products also increases material consumption.

At higher temperatures, the chemical reactions are shortened and the recoating and walkability times are reduced.

The material must always be protected from water during application. During application, care must be taken to ensure that no drops of sweat or water get into the fresh coating surface (foaming). Furthermore, the material must be protected from direct contact with water for approx. 24 hours (at 20°C) after application.

If there is a longer waiting time of >24 hours between the individual work steps or if surfaces already treated with liquid synthetic resins are to be coated again after a longer period of time, the old surface must be cleaned well, sanded thoroughly and vacuumed.

Applications that are not clearly mentioned in this technical data sheet may only be carried out after consultation and written confirmation with or by the application technology department of RCR Flooring Products Italia S.r.l..

Always protect against the effects of moisture from the rear and from pressure, even during use.

Legal information:

Due to the different materials, substrates and deviating working conditions, no guarantee of a work result or liability can be assumed by RCR Flooring Products for whatever reason and / or legal relationship. In addition, the latest general terms and conditions of RCR Flooring Products Italia S.r.l. apply, which can be requested from us or viewed and printed out at www.rinol.it. We expressly reserve the right to make changes to the product specifications.

CE labelling:

DIN EN 13813 "Screed mortars, screed compounds and screeds - Characteristics

and requirements" (Jan. 2003) specifies requirements for screed mortars used for indoor floor constructions.

Synthetic resin coatings and sealers are also covered by this standard. Products that comply with the above standard must be labelled with the CE mark.

 RCR Flooring Products Italia S.r.l. Via Chiarugi 76/U I-45100 Rovigo
05 ¹ EN 13813 SR-B1,5-IR4
1119-CPR-0833 09 EN 1504-2

Synthetic resin screed/coating for indoor use in buildings (structures according to technical data sheets)	
Fire behaviour:	B _{FL} -S1
Water permeability:	NPD ²
Wear resistance (Abrasion Resistance):	NPD ²
Tensile bond strength:	B 1,5
Impact resistance	IR 4
Impact sound insulation:	NPD ²
Sound absorption:	NPD ²
Chemical resistance:	NPD ²

- 1) the last two digits of the year in which the CE marking was affixed
- 2) NPD = No Performance Determined; characteristic value not specified

CE marking: 1504-2

Floors exposed to mechanical loads and related products -2) NPD = no performance determined; must also meet the requirements of DIN EN 13813. DIN EN 1504-2 "Products and systems for the protection and repair of concrete structures - Part 2: Surface protection systems for concrete" specifies the requirements for surface protection methods "water repellent impregnation", impregnation and coating. The relevant data sheet is available on request.

EU Directive 2004/42 (Decopaint Directive):

The maximum VOC content permitted by European Directive 2004/42 (product category IIA/ j type sh) in the ready-to-use stage is 500 g/l (limit 2010). The maximum content of RINOL PA-QC714 in the ready-to-use stage is < 100 g/l VOC.

GIS code: PU 10

Further information on the GIS code is available from Wingis online at <https://www.wingisonline.de>



RCR Flooring Products Italia S.r.l.

Via V. Chiarugi 76/U
I - 45100 Rovigo

Tel.: +39 (0) 425 411 200
Fax: +39 (0) 425 411 222

info.italy@rcrif.com
www.rinol.com

COMPANY WITH
MANAGEMENT SYSTEM
CERTIFIED BY DNV
ISO 9001 • ISO 14001